



Oak Ridge™

Chemical/Equipment



Friendly Foam

Earth friendly..User friendly!

OR-7K-FR

Description

OR7K-FR is a two-component, spray-in-place flexible 100% solids polyurethane/polyurea system. This product provides a flexible but extremely tough monolithic membrane with excellent water and chemical resistance.

Proposed Uses

OR7K-FR is a fast cure, smooth or textured surface, multi-purpose material designed for commercial and industrial roofing systems OR7K-FR meets the requirements of **UL790 (ASTM E-108) in Class B configurations on combustible and non-combustible decks.**

UL Certification/TGRU.R25584

Typical Properties

Property	Test Method	"A"	"B"
Color	N/A	Lt. Yellow	Tan or Gray
Specific Gravity	ASTM D-1638	1.15	1.03
Viscosity	Brookfield VLF	600 cps+100	1000 cps+100
Mixing Ratio	By Weight	53	47
Pounds per gallon	From Spec. Gravity	9.6	8.4

Processing Characteristics

Component Temperature at Spray Head:	
A Component	145°F - 155°F
B Component	145°F - 155°F
Minimum System Pressure	2200 psi
Gel Time	Instantaneous
Cure Time	24 Hours
Product Working Temperature Range	-40°F to 280°F

Physical Properties

Density (pcf)	(ASTM D-1622)	70
Shore A Hardness	(ASTM D-2240)	75 - 85
Tensile Strength	(ASTM D-2370)	2300 psi -4200 psi
Abrasion Resistance (taber) (D-6040)		.03% per 1,000 cycles
Elongation %	(ASTM D-2370)	320% - 605%
Tear Strength	(ASTM D-1004)	400 ppi – 600 ppi
Moisture Vapor Transmission, Perms (E96)		0.025 @ 30 MILS

Application Requirements

OR7K-FR

Sprayed Equipment: Spray equipment must be designed to produce a minimum of 2500 psi with an output of 1.5 gallon per minute. The heating component of the equipment must be able to maintain a temperature at the gun of 150°F. The hose on the equipment must be heated and be rated a minimum of 3,000-psi burst pressure. The spray gun must also be rated at the pressures and throughputs required.

Product Application Parameters:

Property	Test Method	"A"	"B"
Specific Gravity	ASTM D-1638	1.15	1.03
Viscosity	Brookfield LVF	600 cps + 100	1000 cps + 100
Mixing Ratio	By Volume	1	1
Mixing Ratio	By Weight	53	47
Pounds per Gallon	From Spec. Gravity	9.6	8.9
Temp. at Spray Gun	N/A	145°F	145°F
Gel time	N/A	Instantaneous	Instantaneous
Total Cure	N/A	24 Hours	24 Hours
Product Working Temp.	N/A	-40°F to 280°F	-40°F to 280°F
Relative Humidity	N/A	Max 85%	Max 85%

Substrate Parameters: The substrate must be dry! A minimum of 5°F above the dew point is mandatory. The ambient relative humidity should not be above 85%. Pin holing may occur if the above parameters are not strictly followed. Applicator shall check initial climatic conditions. A small area shall be sprayed and check for proper application. Applicator may continue, if upon close inspection, the sprayed sample meets quality standards.

Coverage: The material theoretically will cover 80 square feet at 20 mil dry film thickness. Coverage of the substrate should include a waste factor based on conditions at the site and type of substrate to which the material is being applied.

Call Coating Holdings LTD for technical questions. 1-800-625-9577.

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. COATING HOLDINGS LTD WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES COATING HOLDINGS LTD. EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE COATING HOLDINGS LTD OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.

Suppliers of High performance Foam/Coating and application Equipment

Coating Holding LTD 575 Commercial Ave., Green Lake, WI 54941 800-625-9577 Fax 920-294-6830

www.oakridgepoly.com