



Oak Ridge™

Chemical/Equipment



Friendly Foam
Earth friendly..User friendly!

PRODUCT INFORMATION:

OR93BL2 polyurea spray on bed liner formulation. OR93BL2 Utilizes renewable resources making this product conform to green standards globally. This product provides a flexible but extremely tough monolithic membrane.

PROPOSED USES

OR93BL2 is a fast cure, textured surface, purpose built material designed for automotive applications such as pickup truck bed liners. It exhibits excellent adhesion to most materials and is suitable as a protective-abrasive-impact liner for cementitious, wood, and/or metal surfaces. OR93BL2 exhibits excellent qualities for military applications. This Gen II renewable chemistry has excellent chemical and moisture resistance.

PHYSICAL PROPERTIES:

Shore A Hardness (ASTM D-2240)	85-90
Density (pcf) (ASTM D-1622)	70
Tensile Strength (ASTM D-2370)	2300 psi minimum
Abrasion Resistance (taber) (D-4060)	0.3% per 1,000 cycles
Elongation % (ASTM D-2370)	300% minimum
Tear Strength (ASTM D-1004)	400 ppi minimum
Moisture Vapor Transmission, Perms (E96)	0.025 @ 30 MILS

PROCESSING CHARACTERISTICS:

Component Temperature at Spray Head:	
A Component	145°F-160°F
B Component	145°F-160°F
Minimum System Pressure	2200 psi
Gel Time	Instantaneous
Cure Time	24 hours
Product Working Temperature Range	-20°F to 200°F

Product Application Parameters:

Property	Test Method	“A”	“B”
Specific Gravity	ASTM D-1638	1.15	1.08
Viscosity	Brookfield LVF	600 cps + 100	1000 cps + 100
Mixing Ratio	By Volume	1	1
Mixing Ratio	By Weight	53	47
Pounds Per Gallon	From Spec. Gravity	9.6	8.4
Temp. At Spray Gun	N/A	145°F	145°F
Gel Time	N/A	Instantaneous	Instantaneous
Total Cure	N/A	24 hours	24 hours
Product Working Temp.	N/A	-20°F to 200°F	-20°F to 200°F
Relative Humidity	N/A	MAX 85%	MAX 85%

Application Requirements

Spray Equipment: Spray equipment (Such as Graco XP-1 or greater) must be designed to produce a minimum of 2500 psi with an output of 1.5 gallon per minute. The heating component of the equipment must be able to maintain a temperature at the gun of 150°F. The hose on the equipment must be heated and be rated a minimum of 3,000-psi burst pressure. The spray gun must also be rated at the pressures and throughputs required.

Substrate Parameters: The substrate must be dry! A minimum of 5°F above the dew point is mandatory. The ambient relative humidity should not be above 85%. Pin holing may occur if the above parameters are not strictly followed. Applicator shall check initial climate conditions. A small area shall be sprayed and check for proper application. Applicator may continue, if upon close inspection, the sprayed sample meets quality standards.

Coverage: The material theoretically will cover 80 square feet at 20 mil dry film thickness per gallon. Coverage of the substrate should include a waste factor based on conditions at the site and type of substrate to which the material is being applied.

Call Coating Holdings for technical questions. 800-625-9577

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. Coating Holdings LTD WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY; THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN EXPRESSED OR IMPLIED WARRANTIES AND Coating Holdings LTD EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE Coating Holdings LTD OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.

Suppliers of High performance Foam/Coating and application Equipment

Coating Holding LTD 575 Commercial Ave., Green Lake, WI 54941 800-625-9577 Fax 920-294-6830
www.oakridgepoly.com