

OR 93BL

Bedliner

Description

OR 93BL is highly reactive two component polyurethane-urea hybrid based, solvent free membrane with excellent mechanical characteristics. The system exhibits combined excellent tensile strength, high elongation values, and good wear and tear propagation resistance. The membrane also provides lasting crack bridging properties.

Applied using specialist spray equipment, OR 93BL will begin curing in seconds allowing vertical applications and rapid build up to the desired thickness. OR 93BL retains a high degree of elasticity even at low temperatures.

Typical Component Properties

	Units	Part A	Part B	Test Method
Color		Yellow	Black	Visual
Viscosity	cPs	Liquid	Liquid	Brookfield
		500-800 (at 75°F) (24°C)	400-800 (at 75°F) (24°C)	
Specific Gravity	g/cc	1.14	1.04	

Surface Preparation

All surfaces should be prepared using standard industry practices. If there are any doubts about suitability, a small trial area should be applied.

Mixing Instructions

OR 93BL is designed for use through specialist two component spray equipment. Our Technical Service Department can advise on choice of equipment and optimum processing conditions.

Both components should be raised to the processing temperature and agitated well before use to ensure an even color.

Application Details

Surfaces should be primed, if needed, with the correct primer. OR 93BL is then applied evenly through the correct processing equipment using a 'sweeping' action ensuring a consistent even application is achieved. Over-coating of the membrane can take place after approximately 2 hours of application and up to a maximum of 48 hours.

If applying OR 93BL and the first coat has been allowed to cure for more than 24 hours, then cleaning and re-priming is recommended to ensure adequate adhesion is achieved for the subsequent coat. OR 93BL may be applied down to a temperature of 32°F providing the temperature is rising and at least 6°F above dew point. The membrane will accept light traffic after 2 hours.

Typical Reaction Characteristics

	Units	Results	Test Method
Gel Time	Seconds	6-8	Sprayed
Tack Free Time	Seconds	10-12	Sprayed
Full-Service use	Hours	2	

Values refer to test made with a two-component; high-pressure machine run according to the recommended process conditions above. These are typical values and should not be construed as specifications.

Coverage

80 Sq. Ft. per gallon @ 20 mils

Recommended Process Conditions

The Polyol component must be mixed until homogenous before use. The material should be processed through a two-component high-pressure dosing machine using impingement mixing technology at a feed rate of 0.5 to 2 gallons/minute through a round nozzle.

	Units	Limits
Part B	Vol	1
Part A	Vol	1
Solids Content	%	100
Typical component	Psi	1800-2500

1. These are typical values and should not be construed as specifications.

Handling and Storage

	Units	Part B	Part A
Storage temperature	°F (°C)	59-77 (15-25)	59-77 (15-25)
Storage stability/ Shelf life (1)	Months	6	6

1. Stored in the original sealed drums in a dry place at the recommended temperature

Typical Polymer Properties

	Units	Limits	Test Method
Hardness	Shore D	50	ASTM D2240
Density	g/cc	1.01	DIN 53479
Percent Solids	%	100 (0 g/l VOCs)	
Tensile	psi	5630	ASTM D412
Elongation	%	140	ASTM D412
Tear	pli	340	ASTM D624C
Taber Abrasion	mg/ rev. loss	95/1000	ASTM D3389
Moisture Vapor Permeability	perms	0.02	ASTM E96

These are typical values and should not be construed as specifications.

Product Stewardship

Oak Ridge Foam & Coating Systems, Inc has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success our Product Stewardship program rests with each and every individual involved with Oak Ridge Foam & Coating Systems, Inc products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Safety Considerations

Safety Data Sheets (SDS) are available from Oak Ridge Foam & Coating Systems, Inc. SDS are provided to help customers satisfy their own handling, safety and disposal needs and those that may be required by locally applicable health and safety regulations. SDS are updated regularly, therefore, please request and review the most current SDS before handling or using any product.

Customer Notice

Oak Ridge Foam & Coating Systems, Inc strongly encourages its customers to review both their manufacturing processes and their applications of Oak Ridge products from the standpoint of human health and environmental quality to ensure that Oak Ridge

products are not used in ways for which they are not intended or tested, Oak Ridge personnel are available to answer your questions and to provide reasonable technical support. Oak Ridge product literature including safety data sheets, should be consulted prior to use.

6/20

Manufacturer of High Performance Foam/Coatings & Application Equipment
800-625-9577 920-294-6800 920-294-6830 Fax
575 Commercial Ave., Green Lake, WI 54941 www.oakridgepoly.com