

# OR 74LS

Solvent Based Silicone Roof Coating

## Basic Uses & Description:

OR 74LS is one-component, moisture-curing silicone rubber roof coating systems designed for use on sprayed-in-place polyurethane foam.

The system provides long-term protection because it resists weathering, aging, oxidation, wind-driven sand, rain and snow, the effects of ozone and ultraviolet radiation. The silicone membrane remains flexible even when exposed to extreme temperatures typically found on roofs. The OR 74LS Silicone Roof Coating is available in four standard colors, including:

- White
  - Tan
  - Light Gray
  - Dark Gray
- (Custom colors available upon request at an addition charge)

## Composition and Materials:

OR 74LS is a dispersion of silicone rubber. This coating is a one-part, ready-to-use material that can be applied easily to a dry, frost-free surface, and cures at normal temperature and humidity levels in 1-3 hours by reacting with moisture in the air. For applications with lower-than-normal temperature and humidity levels, expect the cure time to be longer.

## Application:

Surfaces to be coated with OR 74LS must be properly prepared. All surfaces must be clean, dry and free of loose particles. The coating can be applied with standard airless spray equipment or applied by medium nap roller. For small touch-up work a brush may be used.

**Coverage:** 80 Sq. Ft per gallon @ 20 mils

**Suggested Primers:** OR 711, OR PR811, OR E41, wet/green concrete OR T11

## Spray Equipment:

Due to the high viscosity of the material, a high-pressure airless sprayer capable of producing a minimum of 3500 PSI at the spray head should be used. The pump should have a minimum of 3 gallons per minute output rate. Always use components rated for pump pressure. Hoses should be BUNA-N jacketed for prevention of moisture contamination. Hoses should have a minimum I.D. of 3/4" and an adequate working pressure. The spray gun should be high pressure(5000PSI) with reverse-a-clean spray tip., having a minimum orifice of .030 and a 500-fan tip.

## Typical Properties:

	<u>Test</u>	
Appearance		White, dark/light gray and tan
Solids content, percent by volume	ASTM D-1644	82.44%
Solids content, percent by volume	ASTM D-2697	68.9% (+/- 2)
Specific Gravity at 25°C (77°F)		1.31
Tack-free time		10-20 mins.
Cure time		1-3 hours
Volatile Organic Compounds		246 grams/liter
¹20 mils @ 38° (100°F) and 90 % humidity		
²Applies to OR 74LS – white only		
<u>AS CURED</u>		
Durometer hardness-Shore A	ASTM D-2240	70

Tensile strength	ASTM D-412	551 (+/-25)
Elongation, percent	ASTM D-412	186(+/- 10)
Permeability¹ perms	ATSM E-96	7.9
Tensile, set @100% elongation	Nil	
Temp. stability range °C (F°)		-37 to 100 (-35 to 212)
Accelerated weathering, QUV, 5,000 hours	ASTM G-154	No degradation
Flame spread	ASTM E-108	Class A
Initial solar reflectivity²	ASTM C-1549	87
Initial thermal emissivity²	ASTM C-1371	90
SRI value²		113

## Storage and Shelf Life:

OR 74LS has a recommended shelf life of 12 months from date of manufacture when stored in unopened containers and between 400F and 800F. Please refer to product packaging.

## Packaging Sizes:

OR 74LS is available in 50 gallon and 5-gallon containers.

## Maintenance:

The life of the roof may be extended by regularly scheduled maintenance. A roof should typically be inspected at least twice a year. The roof immediately needs to be inspected following severe weather and extraordinary maintenance on roof-mounted equipment.

## Clean Up:

Uncured silicone coating can be cleaned or equipment can be flushed with VM&P Naphtha or Mineral Spirits.

## Limited Warranty Information-Please Read Carefully:

Various warranties may be purchased from Oak Ridge Foam & Coating Systems, Inc. Available warranties include Full System. Limited Warranties that range from 5-20 years. For warranty details, please contact your Oak Ridge Foam & Coating Systems, Inc. Roofing Specialist. Specification Writers: A copy of the Application Specification for this product may be obtained from Oak Ridge Foam & Coating Systems, Inc. Customer Service.

Sales and Customer Support 800-625-9577

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. OAK RIDGE FOAM & COATING SYSTEMS, INC. WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES OAK RIDGE FOAM & COATING SYSTEMS, INC. EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT, ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. OAK RIDGE FOAM & COATING SYSTEMS, INC. REQUIRES APPLICATORS TO BE CERTIFIED THROUGH ATTENDING A ONE- OR TWO-DAY TRAINING SESSION HELD AT OUR GREEN LAKE, WI FACILITY TO SPRAY OR PRODUCTS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE



## OR 74LS

Solvent Based Silicone Roof Coating

PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE OAK RIDGE FOAM & COATINGS SYSTEMS, INC. OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF. 11/21

### **Disclaimer**

The technical data and any other printed information furnished by Oak Ridge Foam & Coating Systems, Inc. (ORFC) are true and accurate to the best of our knowledge. ORFC products conform to in house quality control procedures, tested and should be considered free of defects. The data provided is believed to be reliable and is offered solely for evaluation. The use of the product is beyond the control of the seller; therefore, the buyer assumes all risk whatsoever as to the use of these materials and handling whether done in a matter that is in accordance with the provided posted directions or not. Failure to strictly adhere to recommended procedures and attend a one-day Certified Applicator training, held at the corporate facility located in Green Lake, WI for proper application of ORFC products and materials, shall relieve ORFC of all liability with respect to the materials or the use thereof. This buyer sole and exclusive remedy. All claims concerning product defects must be made in writing within (6) six months of shipment. The absence of such claims in writing during this period will constitute a wave of all claims with respect to such product. This warranty shall be in lieu of any other warranty, expressed, or implied, including, but not limited to any warranty of merchantability or fitness for a particular purpose. 12/20