

OR 93HS

High Solids, Low VOC Silicone Roof Coating

Basic Uses & Description:

OR 93HS Solvent-Free Silicone Roof Coating is a one-component, moisture curing silicone rubber roof coating system designed for use on existing smooth surface BUR, granulated cap sheet, well-adhered acrylic coating, concrete, metal, sprayed-in-place polyurethane foam and various single-ply membrane roofing.

The system provides long-term protection because it resists weathering, aging, oxidation, wind-driven sand, rain and snow, the effects of ozone, ultraviolet radiation and the temperature extremes typically found on roofs. With its high solids content and absence of hydrocarbon solvents, OR 93HS can be applied in excess of 40 mils in a single coat without blistering, while maintaining adhesion. The OR 93HS Solvent Free Roof Coating is available in four standard colors, including:

- White
 - Tan
 - Light Gray
 - Dark Gray
- (Custom Colors available upon request at an additional charge)

This product may contribute towards a variety of LEED credit points.

Suggested Primers: OR 711, OR PR811, OR E41, wet/green concrete, OR T11

Application:

Surfaces to be coated with OR 93HS Coating must be properly prepared. All surfaces must be clean, dry and free of loose particles. The coating can be applied with standard airless spray equipment or applied by medium nap roller. For small touch-up work, a brush may be used.

Clean Up:

Uncured silicone coating can be cleaned or equipment can be flushed with VM&P Naphtha or Mineral Spirits.

Packaging Sizes:

OR 93HS Silicone Roof Coating is available in 55 gallon and 5-gallon containers

Storage and Shelf Life:

OR 93HS has a recommended shelf life of 12 months from date of manufacture when stored in unopened containers and between 400F and 800F. Refer to product packaging.

Composition and Materials:

OR 93HS Silicone Roof Coating is a dispersion of silicone rubber. This coating is a one-part, ready-to-use material that can be applied easily to a dry, frost-free surface, and cures at normal temperature and humidity in 1 to 4 hours by reacting with moisture in the air. For applications with lower-than-normal temperature and humidity levels, expect the cure time to be longer.

Spray Equipment

Due to the high viscosity of the material, a high -pressure airless sprayer capable of producing a minimum of 3500 PSI at the spray gun head should be used. Always use components rated for pump pressure. Hoses should be BUNA-N jacketed for prevention of moisture contamination. Hoses should have a

minimum I. D. of 3/4" and an adequate working pressure. The spray gun should be high pressure (5000 PSI) with reverse-a-clean spray tip, having a minimum orifice of .030 and a 50° fan tip.

Maintenance:

The life of the roof may be extended by regularly scheduled maintenance. A roof should typically be inspected at least twice a year. The roof immediately needs to be inspected following severe weather and extraordinary maintenance on roof-mounted equipment.

Typical Physical Properties

As supplied:	Test	
Appearance	White, dark/light gray, tan	
Solids content-% by volume	ASTMD-1644	92(+/-3)
Flash Point	141°F	
Specific gravity at 25°F (77°F)	1.24	
Tack-free time	1-2 hours	
Cure time	1-4 hours	
Volatile organic compounds	<50 grams/liter	
Durometer hardness, shore A points		
	ASTM D-2240	37
Tensile strength, psi	ASTM D-412	247
Elongation, percent	ASTM D-412	237
Permeability ¹ , perms	ASTM E-96	10.7
Tensile, Set at 100% elongation	Nil	
Temperature stability range, °C (°F)	-37 to 100 (-35 to 212)	
Accelerated weathering, QUV,		
5,000 hours	ASTM G-154	no degradation
Flame spread	ASTM E-108	Class A
Initial solar reflectivity ²	ASTM C-1549	89
Initial thermal emissivity ²	ASTM C-1371	90
SRI value ²	113	
¹ 20 mils at 38°C (100°F) and 90% relative humidity		
² Applies to OR98HS White Only		

Limited Warranty Information-Please Read Carefully:

Various warranties may be purchased from Oak Ridge Foam & Coating Systems, Inc. Available warranties include full system limited warranties that range from 5 to 20 years. For warranty details, please contact your Oak Ridge Foam & Coating Systems, Inc. roofing specialist. 6/20

Substrate

PVC	61 Mils
Modified Bitumen	64Mils
Metal	53Mils
Single ply EPDM	61 Mils
TPO	61 Mils
Concrete	61 mils
Coverage:	80 Sq. Ft. per gallon @ 20 mils

Disclaimer

The technical data and any other printed information furnished by Oak Ridge Foam & Coating Systems, Inc. (ORFC) are true and accurate to the best of our knowledge. ORFC products conform to in house quality control procedures, tested and should be considered free of defects. The data provided is believed



OR 93HS

High Solids, Low VOC Silicone Roof Coating

to be reliable and is offered solely for evaluation. The use of the product is beyond the control of the seller; therefore, the buyer assumes all risk whatsoever as to the use of these materials and handling whether done in a matter that is in accordance with the provided posted directions or not. Failure to strictly adhere to recommended procedures and attend a one-day Certified Applicator training, held at the corporate facility located in Green Lake, WI for proper application of ORFC products and materials, shall relieve ORFC of all liability with respect to the materials or the use thereof. This buyer sole and exclusive remedy. All claims concerning product defects must be made in writing within (6) six months of shipment. The absence of such claims in writing during this period will constitute a wave of all claims with respect to such product. This warranty shall be in lieu of any other warranty, expressed, or implied, including, but not limited to any warranty of merchantability or fitness for a particular purpose. 12/20