



Foam & Coating Systems, Inc.

Badger Black

Product & Features

Badger Black is a single component, liquid applied, bitumen modified, coal tar free, moisture cured polyurethane waterproofing membrane.

Features

- Economical
- User Friendly
- Labor Saving
- Meets the Criteria of ASTM C836 and E96
- Resistant to Bacteria
- User Friendly

Typical Uses

- Foundation Walls
- Basements
- Between Slabs
- Bridges
- Planters
- Shower Pans
- Tunnels

Color

Black

Packaging

5 Gallon Pail, 55 Gallon Drum

Technical Data

Hardness, ASTM D2240	50 ± 5 Shore A
Tear Resistance, Die C, ASTM D624	70 ± 20 pli
Tensile Strength, ASTM D412	450 ± 50 psi
Ultimate Elongation, ASTM D412	2500 ± 50%
Specific Gravity	1.28 ± 0.1
Total Solids by Weight, ASTM D2369	95 ± 3%
Total Solids by Volume, ASTM D2697	94 ± 3%
Viscosity at 80°F	5000 ± 2000 cps
Volatile Organic Compounds, ASTM D-2369-81	0.83 lb/gal
Service Temperature	-25°F to 200°F

Coverage

The approximate coverage is 2 gallons/100 per sqft or 100 sqft/gallon which results in a dry film thickness of 28 mils. Coverage rate will depend on surface roughness and porosity.

Surface Preparation

Joints, Cracks and Flashing:

Apply a stripe coat of Badger Black over all cracks up to 1/16" width. All cracks over 1/16" width must be caulked with a polyurethane sealant.

All metal flashings must be primed with manufacturer's recommended primer.

Mixing

Before application, Badger Black should be thoroughly mixed using a mechanical mixer at slow speed to ensure a homogeneous material. Take care not to allow entrapment of air into the material. Do not mix in an up and down motion.

Application

Badger Black may be applied with a brush, squeegee, trowel, roller or airless sprayer. Over smooth surfaces, such as poured-in-place concrete, apply Badger Black evenly in two 30 mil coats. Badger Black can be applied at any thickness.

A manufacturer approved reinforcing fabric may be applied into the wet coating if desired.

Membrane Protection

As soon as possible after completion of a successful water test or visual inspection and/or repairs, cover membrane with approved protection board or geotextile drainage composite. All horizontal and vertical membrane must be protected.

Curing

At 75°F (24°C) and 50% relative humidity. Typical cure time 12-24 hours.

Cure time will vary depending on temperature and humidity. If more than 48 hours pass between coats the surface must be re-primed.

Badger Black is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in thickness of application. Limit single coat thickness to 30-40 wet mils.

Clean up

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Limitations

Surfaces must be dry, clean and free of foreign matter. Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications. Surface may be slippery when wet. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

Storage

Badger Black has a shelf life of one year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F.

DISCLAIMER AND EXCLUSION OF DAMAGES:

The use of any Oak Ridge Foam & Coating Systems, Inc. ("ORFC") product shall constitute acceptance of the disclaimers and limitations herein set forth. The technical data and any other printed information furnished by ORFC are true and accurate to the best of our knowledge. Data provided is believed to be reliable but is offered solely for evaluation purposes. Use and handling of ORFC's products is beyond the control of the ORFC; therefore, the buyer assumes all risk whatsoever with respect to the use of ORFC products whether used or handled in a matter that is in accordance with the provided posted directions or not.

EXCEPT AS EXPRESSLY SET FORTH IN A WRITTEN WARRANTY AGREEMENT EXECUTED BY AN AUTHORIZED PRINCIPAL OF ORFC, ALL ORFC PRODUCTS ARE PROVIDED "AS IS" WITH NO WARRANTIES OR REPRESENTATIONS WHATSOEVER, EXPRESS OR IMPLIED. ORFC EXPRESSLY DISCLAIMS ALL WARRANTIES AND REPRESENTATIONS, INCLUDING ANY WRITTEN, ORAL, STATUTORY, OR IMPLIED WARRANTIES, OF MERCHANTABILITY,

Manufacturer of High Performance Foam/Coatings & Application Equipment

800-625-9577

920-294-6800

920-294-6830 Fax

575 Commercial Ave., Green Lake, WI 54941

www.oakridgepoly.com



Foam & Coating Systems, Inc.

Badger Black

SATISFACTORY QUALITY, FITNESS FOR ANY PURPOSE, NONINFRINGEMENT, AND ANY WARRANTIES ARISING OUT OF COURSE OF DEALING OR TRADE USAGE. EXCEPT AS PROVIDED HEREIN NO PERSON IS AUTHORIZED TO MAKE ANY REPRESENTATION OR WARRANTY ON BEHALF OF ORFC. NO VERBAL REPRESENTATIONS, STATEMENTS, PROMISES, OR WARRANTIES MADE BY ORFC OR ITS AGENTS SHALL CONSTITUTE WARRANTIES OR SHALL SUPPLEMENT, MODIFY, OR REPLACE ANY OF THE WRITTEN TERMS, CONDITIONS, AND WARRANTIES CONTAINED IN THIS DISCLAIMER OR A WRITTEN WARRANTY AGREEMENT.

RELATING TO ORFC PRODUCTS, WHETHER BASED ON WARRANTY, CONTRACT, TORT (INCLUDING NEGLIGENCE), STRICT LIABILITY OR OTHERWISE, AND WHETHER OR NOT THE PARTY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. ALL CLAIMS FOR DAMAGES RELATED TO AN ORFC PRODUCT MUST BE SUBMITTED TO ORFC IN WRITING WITHIN (6) SIX MONTHS OF PRODUCT SHIPMENT. THE FAILURE TO PROVIDE WRITTEN NOTICE OF ANY CLAIM DURING THIS PERIOD SHALL CONSTITUTE A WAIVER OF ALL CLAIMS WITH RESPECT TO SUCH PRODUCT.

6/24

IN NO EVENT SHALL ORFC BE LIABLE TO ANY PERSON FOR DAMAGES ARISING OUT THE SALE OF OR IN ANY WAY RELATED TO THE USE OF ORFC'S PRODUCTS IN EXCESS OF THE AGGREGATE AMOUNT OF PAYMENTS MADE TO ORFC DURING THE TWELVE (12) MONTH PERIOD PRECEDING ANY SUCH CLAIM FOR DAMAGES. IN NO EVENT SHALL ORFC BE LIABLE FOR ANY PUNITIVE, CONSEQUENTIAL, EXEMPLARY, SPECIAL, INDIRECT, OR INCIDENTAL DAMAGES ARISING OUT OF OR

Manufacturer of High Performance Foam/Coatings & Application Equipment

800-625-9577 920-294-6800 920-294-6830 Fax
575 Commercial Ave., Green Lake, WI 54941 www.oakridgepoly.com