

OR 74LS

Solvent Based Silicone Roof Coating

Basic Uses & Description:

OR 74LS is one-component, moisture-curing silicone rubber roof coating systems designed for use on sprayed-in-place polyurethane foam.

The system provides long-term protection because it resists weathering, aging, oxidation, wind-driven sand, rain and snow, the effects of ozone and ultraviolet radiation. The silicone membrane remains flexible even when exposed to extreme temperatures typically found on roofs. The OR 74LS Silicone Roof Coating is available in four standard colors, including:

- White
- Tan
- Light Gray
- Dark Gray

(Custom colors available upon request at an addition charge)

Composition and Materials:

OR 74LS is a dispersion of silicone rubber. This coating is a one-part, ready-to-use material that can be applied easily to a dry, frost-free surface, and cures at normal temperature and humidity levels in 1-3 hours by reacting with moisture in the air. For applications with lower-than-normal temperature and humidity levels, expect the cure time to be longer.

Application:

Surfaces to be coated with OR 74LS must be properly prepared. All surfaces must be clean, dry and free of loose particles. The coating can be applied with standard airless spray equipment or applied by medium nap roller. For small touch-up work a brush may be used.

Spray Equipment:

Due to the high viscosity of the material, a high-pressure airless sprayer capable of producing a minimum of 3500 PSI at the spray head should be used. The pump should have a minimum of 3 gallons per minute output rate. Always use components rated for pump pressure. Hoses should be BUNA-N jacketed for prevention of moisture contamination. Hoses should have a minimum I.D. of 3/4" and an adequate working pressure. The spray gun should be high pressure(5000PSI) with reverse-a-clean spray tip., having a minimum orifice of .030 and a 50° fan tip.

Typical Properties:

AS SUPPLIED

Appearance	White, dark/light gray and tan	
Solids content, percent by weight	ASTM D-1644	82.44%
Solids content, percent by volume	ASTM D-2697	68.9% (+/-2)
Specific Gravity at 25°C (77°F)	1.31	
Tack-free time	10-20 mins.	
Cure time	1-3 hours	
Volatile Organic Compounds	246 grams/liter	

120 mils @ 38° (100°F) and 90 % humidity

2Applies to OR 74LS – white only

AS CURED

Durometer hardness-Shore A	ASTM D-2240	70
Tensile strength	ASTM D-412	551 (+/-25)
Elongation, percent	ASTM D-412	186(+/- 10)
Permeability ¹ perms	ATSM E-96	7.9
Tensile, set @100% elongation	Nil	
Temp. stability range °C (F°)	-37 to 100 (-35 to 212)	

Accelerated weathering, QUV, 5,000 hours	ASTM G-154	No degradation
Flame spread	ASTM E-108	Class A
Initial solar reflectivity ²	ASTM C-1549	87
Initial thermal emissivity ²	ASTM C-1371	90
SRI value ²	113	

Storage and Shelf Life:

OR 74LS has a recommended shelf life of 12 months from date of manufacture when stored in unopened containers and between 40°F and 80°F. Please refer to product packaging.

Packaging Sizes:

OR 74LS is available in 50 gallon and 5-gallon containers.

Maintenance:

The life of the roof may be extended by regularly scheduled maintenance. A roof should typically be inspected at least twice a year. The roof immediately needs to be inspected following severe weather and extraordinary maintenance on roof-mounted equipment.

Clean Up:

Uncured silicone coating can be cleaned or equipment can be flushed with VM&P Naphtha or Mineral Spirits.

Sales and Customer Support 800-625-9577

DISCLAIMER AND EXCLUSION OF DAMAGES:

The use of any Oak Ridge Foam & Coating Systems, Inc. ("ORFC") product shall constitute acceptance of the disclaimers and limitations herein set forth.

The technical data and any other printed information furnished by ORFC are true and accurate to the best of our knowledge. Data provided is believed to be reliable but is offered solely for evaluation purposes. Use and handling of ORFC's products is beyond the control of the ORFC; therefore, the buyer assumes all risk whatsoever with respect to the use of ORFC products whether used or handled in a matter that is in accordance with the provided posted directions or not.

EXCEPT AS EXPRESSLY SET FORTH IN A WRITTEN WARRANTY AGREEMENT EXECUTED BY AN AUTHORIZED PRINCIPAL OF ORFC, ALL ORFC PRODUCTS ARE PROVIDED "AS IS" WITH NO WARRANTIES OR REPRESENTATIONS WHATSOEVER, EXPRESS OR IMPLIED. ORFC EXPRESSLY DISCLAIMS ALL WARRANTIES AND REPRESENTATIONS, INCLUDING ANY WRITTEN, ORAL, STATUTORY, OR IMPLIED WARRANTIES, OF MERCHANTABILITY, SATISFACTORY QUALITY, FITNESS FOR ANY PURPOSE, NONINFRINGEMENT, AND ANY WARRANTIES ARISING OUT OF COURSE OF DEALING OR TRADE USAGE. EXCEPT AS PROVIDED HEREIN NO PERSON IS AUTHORIZED TO MAKE ANY REPRESENTATION OR WARRANTY ON BEHALF OF ORFC. NO VERBAL REPRESENTATIONS, STATEMENTS, PROMISES, OR WARRANTIES MADE BY ORFC OR ITS AGENTS SHALL CONSTITUTE WARRANTIES OR SHALL SUPPLEMENT, MODIFY, OR REPLACE ANY OF THE WRITTEN TERMS, CONDITIONS, AND WARRANTIES CONTAINED IN THIS DISCLAIMER OR A WRITTEN WARRANTY AGREEMENT.

IN NO EVENT SHALL ORFC BE LIABLE TO ANY PERSON FOR DAMAGES ARISING OUT THE SALE OF OR IN ANY WAY RELATED TO THE USE OF ORFC'S PRODUCTS IN EXCESS OF THE AGGREGATE AMOUNT OF PAYMENTS MADE TO ORFC DURING THE TWELVE (12) MONTH PERIOD PRECEDING ANY SUCH CLAIM FOR DAMAGES. IN



OR 74LS

Solvent Based Silicone Roof Coating

NO EVENT SHALL ORFC BE LIABLE FOR ANY PUNITIVE, CONSEQUENTIAL, EXEMPLARY, SPECIAL, INDIRECT, OR INCIDENTAL DAMAGES ARISING OUT OF OR RELATING TO ORFC PRODUCTS, WHETHER BASED ON WARRANTY, CONTRACT, TORT (INCLUDING NEGLIGENCE), STRICT LIABILITY OR OTHERWISE, AND WHETHER OR NOT THE PARTY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. ALL CLAIMS FOR DAMAGES RELATED TO AN ORFC PRODUCT MUST BE SUBMITTED TO ORFC IN WRITING WITHIN (6) SIX MONTHS OF PRODUCT SHIPMENT. THE FAILURE TO PROVIDE WRITTEN NOTICE OF ANY CLAIM DURING THIS PERIOD SHALL CONSTITUTE A WAIVER OF ALL CLAIMS WITH RESPECT TO SUCH PRODUCT. 6/24