

OR 80SLM

Silver Lining Membrane

Coating Description

100% solids, 2 components, spray applied, pure polyurea elastomer. OR 80SLM is a tough, rapid set; high build coating that is, VOC compliant and moisture tolerant. This coating performs with superior reflective qualities for cool roofing systems. Superior UV & Impact such as hail resistance and Miami Dade Approved.

Primary Application

- Protective coating for metal and built-up roofs
- Protective coating for urethane and expanded polystyrene insulation
- Protective coating for worn out EPDM roofing
- Secondary containment when applied over concrete, wood or geotextiles
- Protective coating for decorative products
- Wearing and waterproofing membrane for pedestrian decks
- Water proofing of buried, protected or unprotected roofs, walks and concrete walls, with or without spray applied foam insulation.
- Vertical or horizontal application
- Approved for external containment liner or food grade dry bulk goods

Chemical Resistance

Good hydrolytic stability to 300° F. Good resistance to inorganic bases, acids and hydrocarbon solvents. Fair resistance to oxygenated and chlorinated solvents. For higher chemical resistance use OR 70SS

Waterproofing Packaging

A 110-gallon kit consists of two (2) 55-gallon drums

Waterproofing storage life

12 months in unopened containers when stored in a dry location at 50-90° F (10-32° C)

Waterproofing Product Advantages

Features

Seamless	Monolithic waterproofing
Rapid set	Back in service sooner
High moisture tolerance	Long open application window
Hi temp range	Wide product applications
Easy high film builds	Reduced labor cost
100% solids	No VOC
Tough film	Abrasion resistant
Long coating life	

Application Data

Substrate must be sound, clean and free of dirt, debris and other contaminants. Oak Ridge Foam & Coating Systems, Inc. primers are used on most substrates. No primer is needed for newly applied or cleaned foam. OR811 or OR711 primer is recommended for bare metal, old foam, concrete, build up roofs, wood and EPDM. Don not apply below 35° F (1.7°C)

Coverage- 80 Sq. Ft per gallon @ 20 Mils

Thoroughly mix Part B of OR 80SLM prior to use and continue to mix. Care should be exercised to prevent cross contamination of the A & B.

Application Equipment

High pressure (2500PSI) plural component proportioning equipment with plural component spray gun. Minimum barrel temperature, 70° F and rising.

Minimum machine temperature 160° F, minimum machine pressure, 2200 psi. Spray tip requirement .01 or .02 size.

Density

Part A	9.09 lbs./gallon
Part B	8.90 lbs./gallon

Typical Physical Properties

	<u>Test</u>	<u>Values</u>
Tensile Strength	ASTM D412	2850
Elongation	ASTM D412	400%
Permanent Set	ASTM D412	10% max
Hardness (shore D)	ASTM D2240	50
Taber abrasion, mg wt. loss C-17)	ASTM D4060	25 (1000 g, 1000 revs,
Taber abrasion, mg wt. loss revs, H-18)	ASTM D4060	630 (1000 g, 1000
Resistant to Cathodic Disbondment	ASTM G8	Pass
Tear Resistance lbs./in	ASTM D624	425
Modulus of Elasticity (psi)	ASTM D638	1250
Ratio A/B	1:1 by volume	
Viscosity A side	2200±500 cps @ 77° F ± 500	
Viscosity B side	1800±50 cps @ 77° F ± 150	
Flash point	Pensky Martins	>200° F (93.3)
VOC	ASTM 3960	0
Low Temp	ASTM D-1737	2@pass
Flexibility	Mandrel Bend	pass
Fire Resistance	(extinguish in <5 Sec)	
Tack Free	To touch	10-20 seconds
Recoat minimum	OR field test	<1 min
Recoat maximum	OR field test	1 hr./after priming
Full Cure	OR field test	5-7 days@70° F
Service Temp	OR field test	-40 + 300° F
Surface application temp	OR field test	40F – 120° F
Water vapor permeability	ASTM E-96	0.01 Perms
Moisture vapor trans	ASTM 4060	20 Perms
Pull test "concrete" failure	ASTM D-7234	375 PSI-concrete
Back to service	Field tests	1 hour
Water absorption	ASTM D-471	.75%
Impact Resistance (Hail)	UL 2218	Class 4

**Test was completed on a film sample with 20 mil thickness. **

Customer support 800-625-9577

DISCLAIMER AND EXCLUSION OF DAMAGES:

The use of any Oak Ridge Foam & Coating Systems, Inc. ("ORFC") product shall constitute acceptance of the disclaimers and limitations herein set forth.

The technical data and any other printed information furnished by ORFC are true and accurate to the best of our knowledge. Data provided is believed to be reliable but is offered solely for evaluation purposes. Use and handling of ORFC's products is beyond the control of the ORFC; therefore, the buyer assumes all risk whatsoever with respect to the use of ORFC products whether



OR 80SLM

Silver Lining Membrane

used or handled in a manner that is in accordance with the provided posted directions or not.

EXCEPT AS EXPRESSLY SET FORTH IN A WRITTEN WARRANTY AGREEMENT EXECUTED BY AN AUTHORIZED PRINCIPAL OF ORFC, ALL ORFC PRODUCTS ARE PROVIDED "AS IS" WITH NO WARRANTIES OR REPRESENTATIONS WHATSOEVER, EXPRESS OR IMPLIED. ORFC EXPRESSLY DISCLAIMS ALL WARRANTIES AND REPRESENTATIONS, INCLUDING ANY WRITTEN, ORAL, STATUTORY, OR IMPLIED WARRANTIES, OF MERCHANTABILITY, SATISFACTORY QUALITY, FITNESS FOR ANY PURPOSE, NONINFRINGEMENT, AND ANY WARRANTIES ARISING OUT OF COURSE OF DEALING OR TRADE USAGE. EXCEPT AS PROVIDED HEREIN NO PERSON IS AUTHORIZED TO MAKE ANY REPRESENTATION OR WARRANTY ON BEHALF OF ORFC. NO VERBAL REPRESENTATIONS, STATEMENTS, PROMISES, OR WARRANTIES MADE BY ORFC OR ITS AGENTS SHALL CONSTITUTE WARRANTIES OR SHALL SUPPLEMENT, MODIFY, OR REPLACE ANY OF THE WRITTEN TERMS, CONDITIONS, AND WARRANTIES CONTAINED IN THIS DISCLAIMER OR A WRITTEN WARRANTY AGREEMENT.

IN NO EVENT SHALL ORFC BE LIABLE TO ANY PERSON FOR DAMAGES ARISING OUT OF THE SALE OF OR IN ANY WAY RELATED TO THE USE OF ORFC'S PRODUCTS IN EXCESS OF THE AGGREGATE AMOUNT OF PAYMENTS MADE TO ORFC DURING THE TWELVE (12) MONTH PERIOD PRECEDING ANY SUCH CLAIM FOR DAMAGES. IN NO EVENT SHALL ORFC BE LIABLE FOR ANY PUNITIVE, CONSEQUENTIAL, EXEMPLARY, SPECIAL, INDIRECT, OR INCIDENTAL DAMAGES ARISING OUT OF OR RELATING TO ORFC PRODUCTS, WHETHER BASED ON WARRANTY, CONTRACT, TORT (INCLUDING NEGLIGENCE), STRICT LIABILITY OR OTHERWISE, AND WHETHER OR NOT THE PARTY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. ALL CLAIMS FOR DAMAGES RELATED TO AN ORFC PRODUCT MUST BE SUBMITTED TO ORFC IN WRITING WITHIN (6) SIX MONTHS OF PRODUCT SHIPMENT. THE FAILURE TO PROVIDE WRITTEN NOTICE OF ANY CLAIM DURING THIS PERIOD SHALL CONSTITUTE A WAIVER OF ALL CLAIMS WITH RESPECT TO SUCH PRODUCT. 6/24