

OR 811

Product Description

OR 811 is a single component polyurethane primer that contains a non – HAP's solvent. OR 811 exhibits high chemical and abrasion resistance for a variety of substrates such as steel, aluminum, stainless steel, galvanized metal, wood, and concrete. Its low viscosity allows it to penetrate porous surfaces, leaving a bubble-free coating. It also exhibits a low sensitivity to substrate moisture, leaving only minimal bubbling when applied to damp surfaces.

Applications

In addition to being used as a primer for enhanced adhesion of other coatings OR 811 is an excellent coating choice for industrial high traffic aisle ways, work cells and warehousing sealer. OR 811 can also be used as an interior coating for wood flooring, furniture, roofing, decking, truck bed liners, pipeline, and tank coatings.

Advantages

- VOC exempt
- Penetrates and seals the surface, leaving a smooth, pinhole and bubble-free coating
- Excellent adhesion to a variety of substrates
- Good physical properties
- Outstanding stability at low temperatures

Application Instructions

OR 811 can be applied using a 1/4" nap roller. Apply as uniformly as possible avoiding excessive back rolling and cross rolling will lessen the chance of bubbling.

OR 811 can be applied using single component spray equipment. Consult with your technical representative for specific equipment requirements.

Thinning

Thinning is recommended with MEK up to 20%.

Mixing

Mixing is not required unless using a pigmented version.

Surface Preparation

1. Previously painted surfaces: Solvent clean to remove all oils, grease and wax. Remove all rust and damaged paint. Feather edge the repair areas. Fill and putty as required. Sand all areas to be painted with 120-180 grit wet or sandpaper. Primer with OR 811.
2. Stainless steel: Solvent wipe, scuff sand or abrasive blast. Prime with OR 811.
3. Steel: Remove all rust, mill scale, and foreign matter. Solvent wipe to remove all oils and grease. Sand blasting is best- if possible. Prime with OR 811.
4. Aluminum: Solvent clean to remove all oil and grease. Sand surface with 120-180 grit sandpaper. Prime with OR 811.
5. Concrete: Laitance, curing compounds, concrete contaminants must be removed. Sand-blast or acid etch areas to be coated. Prime with OR 811.

Coverage

1 Gallon covers 500 ft² @3 mills

On porous surfaces application rate should be 300-500ft² per gallon.

On smooth surfaces application rate should be 600-800ft² per gallon.

Clean up

Before product has cured remove unwanted OR 811 with Methyl Ethyl Ketone (MEK).

Typical Physical Properties	Units	Results
Tensile strength	Psi	3300
Elongation	pli	85%
Tear strength	pli	440
Polyurea topcoat adhesion	psi	>500
Adhesion to concrete	Elcometer	550 psi
Typical film thickness	Mils	3-8
Minimum re-coat time	hours	4
Viscosity at 77° F (25°C)	cps	220
Specific gravity at 77°F (25°C)	g/cm ²	1.19
Flash Point (Cleveland open cup)		>110/>230
Vapor pressure at 77°F (25°C) (mm)		<10-5
Recommend storage temperature		60-100°F (16-38°C)
Shelf life	Un-opened	12 months
Solids by weight		60%
Solids by volume		64%
Abrasion resistance	ASTM D-4060	20 mg weight loss

Color

OR 811 is supplied standard unpigmented and appears amber in color.

OR 811 may be supplied pigmented upon request.

Packaging supplied in

1 Gallon Can, 5 Gallon Pail, 55 Gallon Drum

Limitations

This product is not recommended for immersion service, unless used with a topcoat.

Do not apply this product at ambient or floor temperature below 15°F or over 90°F or if the relative humidity is above 95%.

Handling and storage

The reaction of isocyanates with water leads to the formation of insoluble areas and carbon dioxide gas which can result in pressure buildup inside closed containers. Therefore, extreme care must be taken to ensure containers used for OR 811 remain dry. Containers that have become contaminated with moisture should not be subsequently sealed; otherwise, a hazardous increase in pressure may result. Freshly manufactured OR 811 is an amber liquid. Sedimentation is usually due to contamination from atmospheric moisture or to dimer formation. Reaction from atmospheric moisture can be prevented by storing OR 811 in carefully sealed containers or under a dry nitrogen atmosphere during handling OR 811 must be carefully resealed after each sampling. A small amount of finely divided insoluble solid in the product does not usually cause difficulties in handling or product performance. However, if necessary, the liquid product may be filtered through a suitable inline filter. It is suggested that the filter vessel be of stainless steel with a suitable polypropylene filter bag. The lines should be heated and blown clear with nitrogen after use.

OR 811

DISCLAIMER AND EXCLUSION OF DAMAGES:

The use of any Oak Ridge Foam & Coating Systems, Inc. ("ORFC") product shall constitute acceptance of the disclaimers and limitations herein set forth. The technical data and any other printed information furnished by ORFC are true and accurate to the best of our knowledge. Data provided is believed to be reliable but is offered solely for evaluation purposes. Use and handling of ORFC's products is beyond the control of the ORFC; therefore, the buyer assumes all risk whatsoever with respect to the use of ORFC products whether used or handled in a matter that is in accordance with the provided posted directions or not.

EXCEPT AS EXPRESSLY SET FORTH IN A WRITTEN WARRANTY AGREEMENT EXECUTED BY AN AUTHORIZED PRINCIPAL OF ORFC, ALL ORFC PRODUCTS ARE PROVIDED "AS IS" WITH NO WARRANTIES OR REPRESENTATIONS WHATSOEVER, EXPRESS OR IMPLIED. ORFC EXPRESSLY DISCLAIMS ALL WARRANTIES AND REPRESENTATIONS, INCLUDING ANY WRITTEN, ORAL, STATUTORY, OR IMPLIED WARRANTIES, OF MERCHANTABILITY, SATISFACTORY QUALITY, FITNESS FOR ANY PURPOSE, NONINFRINGEMENT, AND ANY WARRANTIES ARISING OUT OF COURSE OF DEALING OR TRADE USAGE. EXCEPT AS PROVIDED HEREIN NO PERSON IS AUTHORIZED TO MAKE ANY REPRESENTATION OR WARRANTY ON BEHALF OF ORFC. NO VERBAL REPRESENTATIONS, STATEMENTS, PROMISES, OR WARRANTIES MADE BY ORFC OR ITS AGENTS SHALL CONSTITUTE WARRANTIES OR SHALL SUPPLEMENT, MODIFY, OR REPLACE ANY OF THE WRITTEN TERMS, CONDITIONS, AND WARRANTIES CONTAINED IN THIS DISCLAIMER OR A WRITTEN WARRANTY AGREEMENT.

IN NO EVENT SHALL ORFC BE LIABLE TO ANY PERSON FOR DAMAGES ARISING OUT OF THE SALE OF OR IN ANY WAY RELATED TO THE USE OF ORFC'S PRODUCTS IN EXCESS OF THE AGGREGATE AMOUNT OF PAYMENTS MADE TO ORFC DURING THE TWELVE (12) MONTH PERIOD PRECEDING ANY SUCH CLAIM FOR DAMAGES. IN NO EVENT SHALL ORFC BE LIABLE FOR ANY PUNITIVE, CONSEQUENTIAL, EXEMPLARY, SPECIAL, INDIRECT, OR INCIDENTAL DAMAGES ARISING OUT OF OR RELATING TO ORFC PRODUCTS, WHETHER BASED ON WARRANTY, CONTRACT, TORT (INCLUDING NEGLIGENCE), STRICT LIABILITY OR OTHERWISE, AND WHETHER OR NOT THE PARTY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. ALL CLAIMS FOR DAMAGES RELATED TO AN ORFC PRODUCT MUST BE SUBMITTED TO ORFC IN WRITING WITHIN (6) SIX MONTHS OF PRODUCT SHIPMENT. THE FAILURE TO PROVIDE WRITTEN NOTICE OF ANY CLAIM DURING THIS PERIOD SHALL CONSTITUTE A WAIVER OF ALL CLAIMS WITH RESPECT TO SUCH PRODUCT. 6/24